




Premium Grade Duct Tape



| Backing: | PE Coated Cloth | | |
|-----------------|-----------------|----------------------------------|--|
| Adhesive: | Rubber | | |
| Liner: | N/A | | |
| Colors: | Silver, Black | | |
| Specifications: | | Tested in accordance with UL 723 | |
| Standard Sizes: | | 48mm x 55m, 72mm x 55m | |

Applications

- Hanging and seaming poly sheeting
- Sealing and closure tape for poly bags
- Sealing and closure tape for poly bags
- General purpose packaging and repair
- Temporary holding and bundling

| Features | Benefits | | |
|---|--|--|--|
| PE-Coated Cloth Backing | Good balance of tensile strength and tearability | | |
| | Conformable and moisture resistant | | |
| Natural Rubber Based Adhesive | Aggressive high adhesion | | |
| | Superior vertical hold | | |
| Low VOC Content | Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED[®] | | |

Physical Properties

| | • | - | |
|-----------------------|--------------|------------|-------------|
| | Standard UOM | Metric UOM | Test Method |
| Total Thickness | 12 mils | 305 mic | ASTM D-1000 |
| Adhesion to Steel | 93 oz/in | 10.3 N/cm | PSTC-101 |
| Adhesion to Backing | 52 oz/in | 5.7 N/cm | PSTC-101 |
| Tensile Strength | 27 lb/in | 47.3 N/cm | ASTM D-1000 |
| Elongation | 24% | | ASTM D-1000 |
| Operating Temperature | 40 to 200 °F | 4 to 93 °C | |
| VOC Content | <1 g/L | | |

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryplastics.com Nijverheidsstraat 10 2260 Oevel (Westerlo) Belgium 32-014-722500 Fax 32-014-722570 6/18/13